

Ecotran® E1040SEW

Polyphenylene sulfide

Out line : Ecotran E1040SEW is a 40% glass fiber filled PPS compound developed to provide a high strength.

	Method	Unit	E1040SEW
General Information			GF 40% High strength
Physical properties			
Density	ISO 1183/A	g/cm ³	1.67
Water absorption	ISO 62	%	0.02
Mold shrinkage (MD/TD)	ISO 294-4	%	0.30 / 0.60
Mechanical properties			
Tensile strength	ISO 527-1, -2	MPa	210
Tensile elongation at break	ISO 527-1, -2	%	1.8
Flexural strength	ISO 178	MPa	310
Flexural modulus	ISO 178	GPa	14.5
Charpy impact strength (notched/unnotched)	ISO 179/1eA,U	kJ/m ²	9 / 50
Rockwell hardness	ISO 2039/2	R-Scale	121
Thermal properties			
Melting temperature	ISO 11357	°C	280
Heat Deflection temperature, 1.82Mpa	ISO 75-1, -2/A	°C	> 265
Flammability (T=0.3mm)	UL 94	class	V-0
Electrical properties			
Dielectric strength (T=1.0mm)	IEC 60243-1	kv/mm	28
Dielectric constant, 1MHz	IEC 60250	-	3.8
Dielectric factor, 1MHz	IEC 60250	-	0.0016
Comparative tracking index (CTI)	IEC 60112	Volt	175
Arc resistance	ASTM D495	sec.	125
Volume resistivity	IEC 60093	Ohm.cm	10 ¹⁶
Processing Conditions			
Pre-drying		-	130°C / 4hr
Cylinder temperature		°C	280 - 330
Mold temperature		°C	130 - 150

* The information provided in this data sheet is based on HDC Polyall's test method, so it can not be used as guaranteed specification limits.