

Ecotran[®] E2130TM

Polyphenylene sulfide

Outline : Ecotran E2130TM is a 30% glass fiber filled PPS compound developed to provide high toughenss

	Method	Unit	E2130TM
General Information			GF 30% Super tough
Physical properties			
Density	ISO 1183/A	g/cm ³	1.49
Water absorption	ISO 62	%	0.02
Mold shrinkage (MD/TD)_ 100x100x 3mm	HDC Method	%	0.3 / 0.8
Mechanical properties			
Tensile strength	ISO 527-1, -2	MPa	150
Tensile elongation at break	ISO 527-1, -2	%	2.0
Flexural strength	ISO 178	MPa	235
Flexural modulus	ISO 178	MPa	8,800
Flexural elongation at break	ISO 178	%	3.0
Charpy impact strength (notched)	ISO 179/1eA	kJ/m ²	11
Charpy impact strength (unnotched)	ISO 179/1eU	kJ/m ²	60
Thermal properties			
Melting temperature	ISO 11357	°C	280
Coefficient of thermal expansion (MD)	ISO 11359-1, -2	µm/m.°C	15
Heat Deflection temperature, 1.82Mpa	ISO 75-1, -2/A	°C	>260
Flammability (T=1.5mm)	UL94	Class	V-0
Electrical properties			
Dielectric strength (T=1.0mm)	IEC 60243-1	kv/mm	25
Dielectric constant, 1MHz	IEC 60250	-	4
Dielectric factor, 1MHz	IEC 60250	-	0.005
Comparative tracking index (CTI)	IEC 60112	Volt	150
Volume resistivity	IEC 60093	Ohm-cm	10 ¹⁶
Processing Conditions			
Pre-drying		-	130°C / 4hr
Cylinder temperature		°C	280 - 330
Mold temperature		°C	130 - 150

* The information provided in this data sheet is based on HDC POLYALL's knowledge and test method, so it can not be used as guaranteed specification limits.