

ZYTEL® 70G50 ECO-R 311 BLK1

NYLON RESIN

Zytel® 70G50 ECO-R 311 BLK1 incorporates 30% of post-industrial recycled content by weight in the finished product. It is a 50% Glass Reinforced, Heat Stabilized, Polyamide 66 designed for Automotive industry.

Product information

| | | |
|----------------------|-----------------------|-----------|
| Resin Identification | PA66-GF50(R30 | ISO 1043 |
| Part Marking Code |) >PA66-GF50(R30)< | ISO 11469 |

Rheological properties

| | | |
|------------------------------------|-------------|-----------------|
| Moulding shrinkage range, parallel | 0.2 - 0.5 % | ISO 294-4, 2577 |
| Moulding shrinkage range, normal | 0.5 - 0.8 % | ISO 294-4, 2577 |

Typical mechanical properties

| | dry/cond. | | |
|--------------------------------------|-------------------------|-------------------|--------------|
| Tensile modulus | 16500 / - | MPa | ISO 527-1/-2 |
| Tensile stress at break, 5mm/min | 200 / - | MPa | ISO 527-1/-2 |
| Tensile strain at break, 5mm/min | 2 / - | % | ISO 527-1/-2 |
| Flexural modulus | 15500 / - | MPa | ISO 178 |
| Flexural strength | 300 / - | MPa | ISO 178 |
| Charpy impact strength, 23°C | 65 / - | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 10 / - | kJ/m ² | ISO 179/1eA |
| Izod notched impact strength, 23°C | 10 / - | kJ/m ² | ISO 180/1A |
| Poisson's ratio | 0.33 / - ^[C] | | |
| [C]: Calculated | | | |

Thermal properties

| | dry/cond. | | |
|---|-----------|----|----------------|
| Melting temperature, 10°C/min | 260 / * | °C | ISO 11357-1/-3 |
| Temperature of deflection under load, 1.8 MPa | 244 / * | °C | ISO 75-1/-2 |

Physical/Other properties

| | dry/cond. | | |
|--------------------------|-----------|-------------------|----------------|
| Humidity absorption, 2mm | 1.2 / * | % | Sim. to ISO 62 |
| Water absorption, 2mm | 4 / * | % | Sim. to ISO 62 |
| Density | 1590 / - | kg/m ³ | ISO 1183 |

Injection

| | |
|---------------------------------|----------|
| Drying Recommended | yes |
| Drying Temperature | 80 °C |
| Drying Time, Dehumidified Dryer | 2 - 4 h |
| Processing Moisture Content | ≤0.15 % |
| Melt Temperature Optimum | 285 °C |
| Min. melt temperature | 275 °C |
| Max. melt temperature | 295 °C |
| Screw tangential speed | ≤0.2 m/s |
| Mold Temperature Optimum | 100 °C |
| Min. mould temperature | 70 °C |

ZYTEL® 70G50 ECO-R 311 BLK1

NYLON RESIN

Max. mould temperature

120 °C

Characteristics

| | |
|-------------------------|--|
| Processing | Injection Moulding |
| Delivery form | Granules |
| Additives | Contains Recycle |
| Special characteristics | Heat stabilised or stable to heat, Sustainable |

Additional information

Injection molding

Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Processing

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the

ZYTEL® 70G50 ECO-R 311 BLK1

NYLON RESIN

annealing (60-80 °C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

57004267.27005138.21046404

Automotive

OEM

VW Group

VW Group

STANDARD

VW 50127


VW 50133

ADDITIONAL INFORMATION

*Best Fitting Grade To PA66-10, Not Officially Approved

*Best Fitting Grade To PA66-8-A, Not Officially Approved


Stress-strain (dry)



ZYTEL® 70G50 ECO-R 311 BLK1

NYLON RESIN

Secant modulus-strain (dry)



Printed: 2024-11-08

Page: 4 of 4

Revised: 2024-06-24 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2024 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.